

DESCRIPTION

Total thickness	EN 428	mm	5.00
	ASTM F386-02	inch	0.2
Thickness of wearlayer	EN 429	mm	0.55
	ASTM F410-02	inch	0.02
Weight	EN 430	g/sq.m	8260
Tile size	EN 427	mm	
Plank size	EN 427	mm	176 x 1000
	ASTM F 536	inch	6.929" x 39.37"
Number of tiles per package	-	-	
Number of planks per package	-	-	10
Coverage / box		sq.m	1.76
	-	sq.ft.	18.94





CLASSIFICATION

Norm / Product specification	-	-	EN 649
	ASTM F 1700- 04	-	-
European classification	EN 685	class	33 - 42
Fire rating	EN 13 501-1	class	B _{fl} -s1
Fire rating	ASTM E648-08	class	
	CAN/ULC S102.2	-	-
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51 130	class	R9

PERFORMANCE

Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	EN 649	-	T
Type Binder content	ISO 10582	type	I
Dimensional stability	EN 434	%	≤ 0.15
Residual indentation	EN 433	mm	≤ 0.10
Impact sound insulation	EN ISO 717-2	dB	5
Room impact	NF S 31074	dB	77
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR+
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100

CE MARKING

	EN 14041	-	  
		-	